25X1A TWO EIGHT FIVE ONE 25X1A

IN 13048

- 2. ALFA SERIES OF TESTS WERE RUN TWO SIX JAN. USING IN ALL CASES APPROX. ONE ZERO ZERO FT LENGTHS FILM WAS RUN THROUGH. PREVET FOR TWO PASSES, DEVELOPER FOR SIX MIN, SHORTSTOP FOR TWO PASSES, AND HYPO CONSISTING OF SODIUM THIOSULFATE CRYSTALS ACETIC ACID AND POWDERS FIXING BATH HARDENER FOR SIX MIN.
- A. TEST ONE AFTER HYPO WASHING WAS DONE IN THREE BATHS OF FIVE MIN EACH TOTAL ONE FIVE MIN. RESULTS EXCELLENT ALLOWING SPEED SETTING OF TWO ZERO FT/MIN. IN DRYER.
- B. TEST TWO AFTER HYPO WASHING WAS DONE IN FOUR BATHS OF OME FIVE MIN EACH TOTAL SIX MIN. RYSULTS EXTREME STICKINESS IN DRYER.
- C. TEST THREE FOLLOWING FIXING FILM WASHED IN WATER FIVE MIN, PERMAWASH FIVE MIN, WITH ALFA FINAL WASH OF FIVE MIN RESULT EXTREME STICKINESS.

082620100

- D. TEST FOUR REPEAT OF TEST ONE WITH IDENTICAL RESULTS.
- E. TEST FIVE REPEAT OF TEST ONE AND FOUR WITH NEARLY THE SAME RESULT. THERE WAS SOME STICKINESS AT FIRST BUT THIS CLEARED UP ALLOWING SPRED SETTINGS UP TO MEARLY TWO ZERO FT/MIN.
- F. TEST SIX WASHING ACCOMPLISHED IN THREE BATHS ONE EACH FIVE MIN, ONE ZERO MIN, AND ONE FIVE MIN TOTAL THREE ZERO MIN RESULT WAS CONSIDERABLE STICKINESS.
- G. TEST SEVEN WASHING WAS CARRIED OUT FOR ALFA TOTAL OF SIX ZERO MIN IN BATHS OF FIVE MIN ONE ZERO MIN AND THREE OF Approved For Release 2000/04/12 : CIA-RDP61S00750A000400090045-8 ONE FIVE MIN RESULTING IN EXTREME STICKINESS.

- 3. IApproved For Release 2000/04/121:16 R-RDP61500750A000400090045-8 CLEANED PRIOR TO TESTS ONE, FOUR, AND SIX.
- 4. THESE TESTY WERE RUN USING THE SAME CHEMICALS IN ORDER
 TO ISOLATE FOR CONSIDERATION THE RESULTS OF LENGTH OF TIME IN WASH.
 IN MISSION ONE THREE FIVE ONE AND ONE THREE FIVE TWO IT HAD
 BEEN NOTED THAT SHORT PIECES WASHED NINE ZERO MIN CAUSED
 SOME STICKINESS AND ALFA LONG PIECE WASHED SIX ZERO MIN RESULTED
 IN IMPROVED RUNNING THRU DRYER.
- 5. THE RESULTS OF THESE TESTS WILL BE APPLIED AT THE FIRST OPPORTUNITY TO LIQUID CHEMICALS.

| <u>2</u> | 5X1A | | _ | | | | | |
|----------|-------------|--------|-----|---------|------|--------|-----|------|
| CFN: | | | JAN | APPROX | FT | PREWET | MIN | НҮРО |
| SODIUM | THIOSULFATE | ACETIC | ACI | D MIN H | (PO) | FT MIN | | |



